



TEST REPORT

Client: Jones Interiors
 Lortas Road
 New Basford
 Nottingham
 Nottinghamshire
 NG5 1EH

Entry No: 82660

Date received: 01/02/2017

Client's Description: Sample of fabric: HL25/IVY

Test Required: Flammability BS 5867-2: Type B: 2008

Pre-treatment: Tests were made both before and after 5 washes in accordance with BS EN ISO 6330: 2012 wash procedure (3G) at 30 Degrees C followed by line drying.

Conditioning: A minimum of 24 hours at 65+/-5% Relative Humidity, 20+/-2°C

Date Tests Completed: 13/03/2017

Method of Test: BS EN ISO 15025: 2002 Procedure A (surface ignition)

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Flame application time 15 seconds using propane gas

As Received

Face of Fabric tested	Fabric length direction			Fabric width direction		
	1↑	2↓	3↑	4→	5←	6→
Specimen number						
Flame reached an edge (✓ or X)	X	X	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X	X	X

-----End of Page-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Dale Brockbank
 Materials Testing Manager
 13 March 2017

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104



Client: Jones Interiors

Entry No: 82660

After Washing

Face of Fabric tested	Fabric length direction			Fabric width direction		
	1↑	2↓	3↑	4→	5←	6→
Specimen number						
Flame reached an edge (✓ or X)	X	X	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X	X	X

Comments

On the basis of the tests carried out this sample of fabric meets the Type B requirements of BS 5867-2: 2008.

-----End of Document-----